

## PATCHING COMPOUND POLYESTER FIBER REINFORCED

**DESCRIPTION:** PRODUCT NO. 501-W-P is a premium quality elastomeric white patching compound designed for use in the construction of professional roof flashings. This material is a blend of Acrylic polymers with a high solid content.

**USES:** PRODUCT NO. 501-W-P can be used as a patching compound or flashing cement for filling voids, gaps in parapet walls. PRODUCT NO. 501-W-P is also used with polyester membrane to seal around penetrations, drains, or scuppers. PRODUCT NO. 501-W-P is the ideal patching compound for polyurethane foam roofs and skylights.

**SURFACE PREPARATION:** All surfaces to receive PRODUCT NO. 501-W-P white patching compound must be scrubbed clean and free from oil, grease, rust, scale, loose paint and dirt.

**APPLICATION:** PRODUCT NO. 501-W-P should be applied with a stiff brush at a thickness of 1/16" to 1/8" in conjunction with a polyester membrane for reinforcement. Apply PRODUCT NO. 501-W-P liberally in joint areas, seams or cracks. Work material to be a feather edge to allow for surface drainage. While PRODUCT NO. 501-W-P patching compound is white, it is recommended that the patching compound be coated by one of TUCSON RUBBERIZED COATINGS top coatings to protect the patch from the UV rays. Allow 24 hours before coating over PRODUCT NO. 501-W-P.

**KEEP PRODUCT FROM FREEZING.**  
**DO NOT APPLY TO ANY SURFACES THAT CONTAIN SILICONE.**

**CLEAN-UP:** Clean brushes, tools and other equipment with soapy water immediately after use. Dried film may require paint remover.

**HANDLING PRECAUTIONS:** Product safety information required for safe use is not included. Before handling, read product safety data sheets and container labels for safe use and for physical and health hazard information. Safety data sheets are available on the TRC website at [www.rubberized.com](http://www.rubberized.com). You can also obtain a copy from one of our local TRC stores.

**LIMITED WARRANTY AND DISCLAIMER:** To the best of our knowledge, the technical data contained herein is true and accurate at the date of issuance and is subject to change without prior notice. User must contact TRC to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. Liability, if any, is limited to replacement of product unless installed by an approved contractor in accordance with TRC warranty procedures and program. For limited manufacturer's warranty and disclaimer information, visit our website at: [www.rubberized.com/resources/warranties/](http://www.rubberized.com/resources/warranties/)

**PHYSICAL PROPERTIES:**

Coating Type	Elastomeric Patching Compound
Solids by Weight (%)	73% (±3)
Solids by Volume (%)	54% (±3)
Weight per Gallon	11 lbs.
Drying Time	At 50% relative humidity and 70°F; Touch: 4 hrs, Firm: 8 hrs
Flammability	None
VOC	< 150 grams/liter
Elongation	> 425%
Tensile Strength	> 350 PSI
Viscosity	130 KU
Adhesion	Excellent Adhesion to Polyurethane Foam, EPDM, TPO
Tear Resistance	> 130 lbf/in.
Water Swelling	After 7 days < 9%
Reflectivity	85%

\*NOTE: Percentages stated are + or - 5%

Approx. Shipping Weights:  
(All approximate weights include container)  
5 Gallons 61 lbs.  
3.5 Gallons 43 lbs.  
1 Gallon 12 lbs.